

**Metallic Sieve Final Weighted Assay Results Influenced by the Coarse Fraction
(+100 mesh) Assay Showing % Increase/Decrease relative to the Fine (-100 mesh)**

Hole Number	Width meters	Weight of Fine Fraction Wt -100 grams	Weight of Coarse Fraction Wt +100 grams	Fine Fraction Assay-1 Au -100 g/t	Fine Fraction Assay-2 Au -100 g/t	Fine Fraction Assay-3 Au -100 g/t	Coarse Fraction Assay-4 Au +100 g/t	Final Assay Result Au g/t	% Increase >highest Au-100 mesh assay	% decrease < lowest Au-100 mesh assay
		TR-11-07	1.15	2168.00	20.94	1.71	1.58	1.65	38.50	2.00
TR-11-22	1.05	2068.80	23.89	2.78	2.91	2.85	39.77	3.69	21.14	
TR-11-27	1.30	2344.00	34.25	3.39	3.33	3.36	45.50	3.97	14.61	
TR-11-47	0.95	1759.00	34.97	0.69	0.55	0.62	8.74	0.78	11.54	
TR-11-35	0.70	731.00	34.17	0.38	0.38	0.38	0.79	0.40	5.00	
TR-11-44	0.40	795.00	13.78	0.96	1.13	1.05	25.54	1.46	22.60	
TR-11-47	0.95	1771.00	27.66	5.45	5.69	5.57	18.31	5.77	1.39	
TR-11-48	0.75	1355.00	18.41	15.84	15.53	15.69	106.60	16.90	6.27	
TR-11-48	0.20	427.00	30.55	7.30	7.10	7.20	15.05	7.72	5.44	
TR-11-56	1.50	2821.00	26.99	3.22	3.43	3.33	145.82	4.68	26.71	
TR-11-57	0.75	1604.00	27.75	14.64	15.02	14.83	53.01	15.48	29.72	
TR-11-57	0.75	1200.00	20.90	1.99	2.09	2.04	50.95	2.88	27.43	
TR-11-58	0.75	1416.00	24.35	1.44	1.34	1.39	7.03	1.49	3.36	
TR-11-61	1.50	3012.00	27.60	28.63	28.35	28.49	535.75	33.10	13.50	
TR-11-62	0.30	630.00	32.75	33.22	33.60	33.41	127.00	38.03	11.65	
TR-11-63	0.40	547.00	24.64	3.02	3.26	3.14	7.20	3.32	1.81	
TR-11-64	1.10	1995.00	32.51	5.45	5.25	5.35	34.01	5.81	6.20	
TR-11-65	1.10	1904.00	33.27	3.67	3.50	3.59	12.21	3.73	1.07	
TR-11-67	0.15	284.00	24.12	1.20	1.30	1.25	0.51	1.19		0.84
TR-11-67	0.40	700.00	28.34	37.34	36.62	36.98	701.66	62.83	40.57	
TR-11-87	0.55	2396.00	28.32	<0.03	<0.03	<0.03	5.90	0.07	57.14*	
TR-11-72	0.20	383.00	30.64	0.34	0.34	0.34	<0.03	0.31		9.68
TR-11-73	0.95	1572.00	28.48	39.60	41.14	40.34	124.39	41.87	1.74	
TR-11-74	0.80	1711.00	30.12	<0.03	<0.03	<0.03	14.33	0.25	88.00*	
TR-11-78	1.45	2557.00	33.09	12.00	11.73	11.87	151.72	13.65	12.09	
TR-11-86	0.85	592.00	19.51	0.27	0.27	0.27	1.37	0.31	12.90	
TR-11-89	0.85	703.00	19.61	5.49	5.42	5.46	13.51	5.67	3.17	
TR-11-90	0.45	1063.00	23.96	11.55	11.93	11.74	37.41	12.31	3.09	
TR-11-91	0.70	1065.00	15.42	12.99	13.20	13.10	48.79	13.60	2.94	
TR-11-97	0.45	856.00	26.98	5.52	5.11	5.32	21.05	5.80	4.83	
TR-11-98	0.50	1036.00	23.00	10.46	10.05	10.26	33.53	10.76	2.79	
TR-11-119	0.70	995.00	16.72	0.14	0.17	0.16	6.34	0.26	34.61	
TR-11-119	0.85	532.00	27.47	37.75	40.80	39.28	84.03	41.47	1.62	
TR-11-120	1.35	2225.00	19.68	0.34	0.34	0.34	2.74	0.36	5.56	
TR-11-111	1.10	1601.00	30.85	18.75	19.71	19.23	86.47	20.50	3.85	

***0.03g/t used as highest gold assay of -100 mesh**